



# DEUSET REPAIR

**(High Quality Cementations Repair Mortar (Single Pack))**

## **DESCRIPTION:**

**DEUSET - REPAIR** is polymer modified cementitious repair mortar for hand application to light repairs. When mixed with recommended amount of clean water, it forms a grey trowellable mortar, which is suitable for interior or exterior applications on to vertical and overhead repairs.

Concrete repair product is specially formulated to produce a shrinkage free mortar giving a smooth finish with excellent adhesion and good water resistant properties.

## **FEATURES:.**

- Premixed Powder – requires only on site addition of water.
- Shrinkage compensating
- Excellent compressive strength
- High bonding strength to prepared surfaces.
- Durable, low permeability and weather proof
- Resistant to carbonation and chlorides attack.



## **TYPICAL PROPERTIES:**

Test method	Typical result
Compressive strength BS 1881 : Pt 116	>35 N/mm <sup>2</sup> at 1 day >50 N/mm <sup>2</sup> at 3 days >60 N/mm <sup>2</sup> at 7 days >70 N/mm <sup>2</sup> at 28 days
Indirect tensile strength (BS 1881 : 1Pt 117)	>4.9N/mm <sup>2</sup>
Flexural strength 1 day (BS 6319 Pt 7) 7 days 28 days	>5 N/mm <sup>2</sup> >9 N/mm <sup>2</sup> >12N/mm <sup>2</sup>
Tensile strength 1 day (BS 6319 Pt 3) 7 days 28 days	>2.5 N/mm <sup>2</sup> >4 N/mm <sup>2</sup> >6N/mm <sup>2</sup>
Bond strength (BS 1881 Pt 207)	>2N/mm
Water permeability (Din 1048)	>7N/mm

## **INSTRUCTIONS FOR USE:**

### **1. Surface Preparation**

The surface of the concrete to be repaired should be sound, clean and uncontaminated. The decayed or damaged area should be saw cut, keeping the sides of the area as square as possible. Loose materials must be removed carefully using suitable means such as sharp tools or chipping hammer. If the reinforcement is corroded make sure that the back of the steel is completely exposed. Then clean the steel to bright metal condition.



## 2. Priming

A. Reinforcement steel: on completion of the cleaning, prime the clean reinforcement steel using Zinc rich primer

B. Concrete: In the event of severe concrete damage due to chloride attack, it is recommended to use a bonding coat before applying . To achieve optimum bond between fresh and cured section, **DEUSET REPAIR** should be applied when the bonding agent is tacky.

## 3. Mixing

**DEUSET REPAIR** can be mixed by hand or mechanical means. Quantities not greater than 10 Kg may be mixed at a time. Slowly add the **DEUSET REPAIR** powder to clean and gauged water, working well to produce a smooth mortar. The consistency of the mix can be adjusted by the addition of more powder or water as necessary.

## 4. Placing & finishing

Whilst the primer is still tacky, apply the mortar mix and compact well. Application can be with trowel or a rubber hand glove to paste the material in place. **DEUSET REPAIR** can be applied to desired thickness in layers on vertical and overhead surfaces. High build application can be achieved by using a formwork. While applying multiple layers, the previous layer should be cross hatched and allowed to set before applying the next coat.

**DEUSET REPAIR** should be cured in accordance with good concrete practice by applying a suitable curing membrane or by covering the work with properly secured plastic sheeting. Protection against rapid drying from wind, sun or excessive heat is necessary.



### **CLEANING:**

Clean all tools with water immediately after use

### **HEALTH & SAFETY**

As with all construction chemical products caution should always be exercised. Protective clothing such as gloves and goggles shall be worn. Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

### **PACKING:**

**DEUSET REPAIR** is available in 25 Kg. bags.

### **STORAGE:**

Store under cover, out of direct sunlight and protect from extreme temperatures. In tropical climates the product must be stored in air – conditioned environment. Shelf life is up to 12 months when stored as per recommendations.

### **NOTE:**

*All information is given in good faith on the results gained from experience and tests. However, all recommendations or suggestions are made without guarantee since we don't have any control on site conditions and its uses.*